



# SUPER LUBE® SILICONE LUBRICATING GREASE WITH SYNCOLON® (PTFE)



SUPER LUBE® SILICONE LUBRICATING GREASE WITH SYNCOLON® (PTFE)

Super Lube® Silicone Lubricating Grease with Syncolon® (PTFE) is a non curing Silicone compound ideal for sealing, protecting and insulating electrical components and connectors.

Super Lube® Silicone Lubricating Grease with Syncolon® (PTFE) is waterproof and protects against moisture and other contaminants in electrical connections.

Super Lube® Silicone Lubricating Grease with Syncolon® (PTFE) is translucent white, clean and clear in appearance and exhibits high dielectric strength and is compatible with most plastics.

Super Lube® Silicone Lubricating Grease with Syncolon® (PTFE) will not harden, dry out or melt.



Part No.	Description
92003	3oz Tube
92005	5# Pail
92150	400gr Cartridge
92016	400gr Can
92030	30# Pail
92400	400# Drum
97008	8oz Tube*

\*Also called Silicone Brake Grease

## Super Lube® Silicone Lubricating Grease With Syncolon® (PTFE)

### Typical Properties

- ▶ Lubricating brake parts
- ▶ Weather stripping
- ▶ Trunk seals
- ▶ Speedometer cables
- ▶ Window channels
- ▶ Hood strips & pads
- ▶ Rubber gaskets
- ▶ High dielectric strength
- ▶ Wide temperature range
- ▶ Excellent heat transfer efficiency
- ▶ Viscosity stable
- ▶ Superior conductive quality
- ▶ Thermally stable
- ▶ Will not react to rubber or plastic
- ▶ Non-toxic



Synco Chemical Corporation - Super Lube®  
 24 DaVinci Drive, Bohemia, NY 11716  
 Tel: (631) 567-5300 / Fax: (631) 567-5359  
 Email: [info@super-lube.com](mailto:info@super-lube.com) / [www.super-lube.com](http://www.super-lube.com)





# SUPER LUBE® SILICONE LUBRICATING GREASE WITH SYNCOLON® (PTFE)

Typical Properties		
Test	Test Method	Rating
Color		Translucent White
Temperature Range		-40°F to 500°F
Penetration, unworked Worked 60 maximum	ASTM D217	280
Bleed, 24 hrs/200°F (392°C) Percent maximum	CTM 0033A	3%
Melting point		No melt
Specific gravity @ 25°C (77°F)	ASTM D1298	1.05
FDA Recognition 21 CFR 175.3000		Yes
U.S.D.A / NSF Registered		H1
Dielectric strength volts/mil, 50 mil gap	CTM 0114	400
Volume Resistivity ohm-cm @ 23°C (73°F)		1X10 <sup>15</sup>



Synco Chemical Corporation - Super Lube®  
 24 DaVinci Drive, Bohemia, NY 11716  
 Tel: (631) 567-5300 / Fax: (631) 567-5359  
 Email: [info@super-lube.com](mailto:info@super-lube.com) / [www.super-lube.com](http://www.super-lube.com)

